

GB Application

For the levelling and repair of

1. Concrete and cement layers and for the creation of gap-levelling layers before fixing tiles on floors.
2. Concrete, masonry, plaster (P II and P III) before fixing tiles, painting and coating walls. For layer thicknesses 5-30 mm. Indoors and outdoors.

Preparing the substrate

The substrate must be load-bearing, clean and free from separating substances, e.g. formwork release oil. Remove cement skin and paint. Roughen extremely smooth surfaces. Concrete must be older than 3 months, cement layers, cement and lime plaster must be sufficiently stable.

How-to-use

Water consumption: 25 kg : approx. 5.0 l water. **Maturing time:** 5 minutes. Stir again. Thin out with a levelling trowel, then apply in the required layer thickness. It is also possible to actuate the grout. **Reworking:** after approx. 1 hour. Protect fresh material from sunlight and drying out too quickly. Before laying natural stone slabs, allow to dry completely.

Application temperature: > 5 °C. **Pot time:** approx. 35 minutes. **To be walked on/laying tiles:** after 3 hours. **Painting/coating the wall:** after drying. All times given are based on 20 °C and 65 % rel. humidity. Higher temperatures shorten and lower temperatures increase the processing and drying time. The technical data may be subject to change. **Storage life:** in closed, original containers, 12 months. Store dry. **Disposal:** recycle empty containers.

Please take note of details in the Harmful Substances Section and in the Technical Instructions Sheet.